

STANDARD SPECIFICATION SHEET

SBR-1502

Chemtech Product Code 59

<u>Properties</u>	<u>Specifications</u>
Appearance	: Non-pollution light yellow rubber block, no coke particles, silt and mechanical admixture
Volatiles %	: Max. 0.60
Organic –acid content %	: 4.50 – 6.75
Soap content, %	: Max. 0.50
Bound Styrene Content, %	: 22.5 – 24.5
Mooney Viscosity (Raw Rubber), ML (1+4) 100°C	: 45 - 55
Moony Viscosity (Compound Rubber), ML (1+4) 100°C	: Max. 93
Moludus at 300% (145°C) /MPa, 25min	: 15.2 – 19.1
35min	: 20.6 ± 2.0
50min	: 21.5 ± 2.0
Tensile Strenght (145°C, 35 min)/MPa	: Min. 25.5
Elongation at break (145°C, 35 min.), %	: Min. 340

Standard packaging

In 35kg net bags, palletized.1 Fcl=17.64mt. Other types of packaging available upon request.

MP/130724

CHEMTECH B.V.

Roemer Visscherstraat 18-II, 1054 EX Amsterdam, The Netherlands

T: +31-20-671 5656, F: +31-20-341 6944, E: info@chemtechbv.com, W: www.chemtechbv.com